



# Status of U.L. approvals, Product Certified for Canada included

LATI S.p.A. - updated - November 2011

file LATI: E 54080 - QMFZ2 , QMFZ8

## UL FOOTNOTES

- |   |   |
|---|---|
| <ul style="list-style-type: none"> <li>(a) indicates glass loadings from 1-30 percent</li> <li>(b) indicates glass loadings from 6-34 percent</li> <li>(c) indicates glass loadings from 5-30 percent</li> <li>(d) indicates glass loadings from 1-29 percent</li> <li>(e) indicates glass loadings from 20-40 percent</li> <li>(f2) Subjected to one or more of the following tests: accordance with UL 746C, where the acceptability for</li> <li>(g) indicates glass loadings from 26-49 percent</li> <li>(h) indicates glass loadings from 16-34 percent</li> <li>(i) indicates glass loadings from 10-30 percent</li> <li>(k) indicates glass loadings from 20-30 percent</li> </ul> | <ul style="list-style-type: none"> <li>(l) indicates glass loadings from 16-29 percent</li> <li>(m) indicates glass loadings from 16-24 percent</li> <li>(n) indicates glass loadings from 26-34 percent</li> <li>(p) indicates glass loadings from 36-49 percent</li> <li>(s) indicates glass loadings from 11-49 percent</li> <li>(q) Optional marking consisting of a generic indication of color (English or Italian) followed by an</li> <li>(r) Optional marking consisting of an alphanumeric code (consisting of 1 or 2 letters followed by one number) referring to manufacturing process information.</li> <li>(u) recognition valid up to 50% regrind</li> <li>(@) all color except black</li> </ul> |
|---|---|



(1-30) indicates MFI from 1-30 g/10<sup>1</sup>

LATI Products listed in UL file E54080 meet US and Canadian requirements.

## R.T.I.

Product	Material	Colors	Min Thk mm	UL 94 Flame Class	Elec		Mech		H W I	H A I	H V T R	D 4 9 5	C T I	G W I T	G W F I
					With Imp	w/o Imp									
PA66	Latamid 66 (q) (r)	ALL	0.75	V-2	65	65	65	-	-	-	-	-	-	-	-
	Latamid 66 PX15 (q) (r)	BK	0.86	HB	65	65	65	-	-	-	-	-	-	-	-
			0.75	HB	105	80	100	4	0	-	-	-	-	-	-
	Latamid 66 H2 G/25 (q) (r)	ALL	1.50	HB	105	80	110	2	0	-	-	-	-	-	-
			3.00	HB	105	80	110	1	0	1	6	1	-	-	-
	Latamid 66 H2 G/(g) (q) (r) (see notes)	ALL	0.75	HB	105	80	100	4	0	-	-	-	-	-	-
			1.50	HB	105	80	105	2	0	-	-	-	-	-	-
			3.00	HB	105	80	105	1	0	1	6	1	-	-	-
	Latamid 66 H2 G/30 (q) (r)	ALL	0.75	HB	105	80	100	4	0	-	-	-	-	-	-
			1.50	HB	105	80	105	2	0	1	-	-	-	-	-
			3.00	HB	105	80	105	1	0	1	6	1	-	-	-
	Latamid 66 H2 G/50 (q) (r)	ALL	0.75	HB	105	85	100	3	0	-	-	-	-	-	-
			1.50	HB	105	85	105	1	0	-	-	-	-	-	-
			3.00	HB	105	85	105	0	0	0	6	0	-	-	-
	Latamid 66 H2 G/60 (q) (r)	BK	0.75	HB	65	65	65	-	-	-	-	-	-	-	-
	Latamid 66 VH2 G/15 (q) (r)	NC,BK	0.75	HB	130	110	130	3	0	-	-	-	-	-	-
			1.50	HB	130	120	130	2	0	-	-	-	-	-	-
			3.00	HB	130	120	130	0	0	1	6	2	-	-	-
	Latamid 66 VH2 G/(m) (q) (r) (see notes)	NC,BK	0.75	HB	115	90	120	4	0	-	-	-	-	-	-
			1.50	HB	120	95	120	2	0	-	-	-	-	-	-
			3.00	HB	125	95	125	0	0	0	6	2	-	-	-
	Latamid 66 VH2 G/25 (q) (r)	NC,BK	0.71	HB	115	90	120	4	0	-	-	-	-	-	-
			1.50	HB	120	95	120	2	0	-	-	-	-	-	-
			3.00	HB	125	95	125	0	0	0	6	2	-	-	-
	Latamid 66 VH2 G/(n) (q) (r) (see notes)	NC,BK	0.71	HB	115	90	120	4	0	-	-	-	-	-	-
			1.50	HB	120	95	120	2	0	-	-	-	-	-	-
			3.00	HB	125	95	125	0	0	0	6	2	-	-	-
	Latamid 66 VH2 G/30 (q) (r)	ALL	0.71	HB	115	90	120	4	0	-	-	-	-	-	-
			1.50	HB	120	95	120	2	0	-	-	-	-	-	-
			3.00	HB	125	95	125	0	0	0	6	2	-	-	-
Latamid 66 VH2 G/35 (q) (r)	NC,BK	0.71	HB	115	115	120	4	0	-	-	-	-	-	-	
		1.50	HB	120	120	120	1	0	-	-	-	-	-	-	
		3.00	HB	125	120	125	0	0	0	6	1	-	-	-	
Latamid 66 VH2 G/(p) (q) (r) (see notes)	NC,BK	0.71	HB	115	115	120	4	0	-	-	-	-	-	-	
		1.50	HB	120	120	120	1	0	-	-	-	-	-	-	
		3.00	HB	125	120	125	0	0	0	6	1	-	-	-	
Latamid 66 VH2 G/50 (q) (r)	NC,BK	0.71	HB	115	120	120	4	0	-	-	-	-	-	-	
		1.50	HB	120	120	120	0	0	-	-	-	-	-	-	
		3.00	HB	125	120	125	0	0	0	6	1	-	-	-	
Latamid 66 S/30 (q) (r)	ALL	0.75	HB	65	65	65	-	-	-	-	-	-	-	-	
		0.71	HB	120	95	120	4	0	-	-	-	-	-	-	
Kelon A H CE/40 (q) (r)	ALL	1.50	HB	120	95	120	2	0	-	-	-	-	-	-	
		3.00	HB	125	95	125	3	0	3	6	1	-	-	-	

Product Material		R.T.I.														
		Colors	Min Thk mm	UL 94 Flame Class	Elec			Mech		H W	H A	H V	D 4	C T	G W	G W
					With Imp	w/o Imp										
<b>Latamid 66 H-V0 (q) (r)</b>		NC	0.41	V-0	65	65	65	-	-	-	-	-	-	-	-	
			0.81	V-0	125	75	75	4	0	-	-	-	-	-	-	
		ALL	1.50	V-0	125	75	75	3	0	-	-	-	-	-	-	
			3.00	V-0	125	80	85	1	0	0	5	0	-	-	-	
<b>Latamid 66 H2PX30-V0 (q) (r)</b>		ALL	0.71	V-0	65	65	65	-	-	-	-	-	-	-	-	
		ALL	0.40	V-2	-	-	-	-	-	-	-	-	-	-	-	
		NC,WT,RD	0.75	V-0	-	-	110	4	0	-	-	-	-	-	-	
		BK	0.75	V-1	-	-	110	4	0	-	-	-	-	-	-	
		NC,WT,RD	0.90	V-0	130	-	110	4	0	-	-	-	-	-	-	
		BK	0.90	V-1	130	-	110	4	0	-	-	-	-	-	-	
<b>Latamid 66 H2PX-V0 (q) (r)</b>		NC,WT,RD	1.00	V-0	130	-	110	4	0	-	-	-	775	960		
		BK	1.00	V-1	130	-	110	4	0	-	-	-	775	960		
			1.50	V-0	130	-	110	3	0	-	-	-	775	960		
		ALL	2.00	V-0	130	-	110	3	0	-	-	-	775	960		
			3.00	V-0	130	-	110	0	0	-	-	2	-	-		
<b>Latamid 66 BH-V0 (q) (r)</b>		ALL	0.75	V-0	65	95	110	-	-	-	-	-	-	-		
			0.90	V-0	130	95	110	-	-	-	-	-	-	-		
			3.00	V-0	130	95	110	-	-	-	-	-	-	-		
<b>Latamid 66 H2PX-V2 (q) (r)</b>		ALL	0.75	V-2	65	95	110	-	-	-	-	-	-	-		
			0.90	V-2	125	95	110	-	-	-	-	-	-	-		
			1.00	V-2	125	95	110	-	-	-	-	-	850	850		
			2.00	V-2	125	95	110	-	-	-	-	-	850	960		
			3.00	V-2	125	95	110	-	-	-	-	-	850	960		
<b>Latamid 66 BG/20-V (q) (r)</b>		ALL	0.75	V-0	65	65	65	-	-	-	-	-	-	-		
<b>Latamid 66 G/20-V0 (q) (r)</b>		ALL	1.50	V-1	65	65	65	-	-	-	-	-	-	-		
			3.00	V-0	65	65	65	-	-	-	-	-	-	-		
<b>Latamid 66 H2 G/05-V0 (q) (r)</b>		ALL	0.81	V-0	110	80	95	4	0	-	-	-	-	-		
			1.50	V-0	110	80	100	2	0	-	-	-	-	-		
			3.00	V-0	110	80	105	1	0	1	6	2	-	-		
<b>Latamid 66 H2 G/(b)-V0 (q) (r)</b> <i>(see notes)</i>		ALL	0.81	V-0	110	80	95	4	-	-	-	-	-	-		
			1.50	V-0	110	80	100	2	0	-	-	-	-	-		
			3.00	V-0	110	80	105	1	0	1	6	2	-	-		
<b>Latamid 66 H2 G/25-V0 (q) (r)</b>		ALL	0.81	V-0	110	85	110	4	0	-	-	-	-	-		
			1.50	V-0	110	85	110	2	0	-	-	-	-	-		
			3.00	V-0	110	85	110	1	0	1	6	2	-	-		
<b>Latamid 66 H2 G/35-V0 (q) (r)</b>		ALL	0.81	V-0	115	105	110	0	1	-	-	-	-	-		
			1.50	V-0	115	105	120	0	0	-	-	-	-	-		
			3.00	V-0	115	105	120	0	0	1	6	2	-	-		
<b>Latamid 66 H2 G/25-V0KB (q) (r)</b>		NC,BK	0.75	V-0	100	75	75	3	0	-	-	-	-	-		
			1.50	V-0	100	80	80	1	0	-	-	-	-	-		
			3.00	V-0	100	85	85	1	0	1	6	1	-	-		
<b>Latamid 66 H2 G/35-V0KB (q) (r)</b>		NC,BK	0.75	V-0	105	75	75	3	0	-	-	-	-	-		
			1.50	V-0	105	85	85	1	0	-	-	-	-	-		
			3.00	V-0	105	85	85	1	0	1	6	1	-	-		
<b>Latamid 66 H2 G/15-V0KB1 (q) (r)</b>		ALL	0.75	HB	105	75	75	2	0	-	-	-	-	-		
			1.50	V-0	105	75	75	1	0	-	-	-	-	-		
			3.00	V-0	105	85	85	0	0	1	6	1	-	-		
<b>Latamid 66 H2 G/(h)-V0KB1 (q) (r)</b> <i>(see notes)</i>		ALL	0.75	HB	130	115	140	3	0	-	-	-	-	-		
			1.50	V-0	130	115	140	1	0	-	-	-	-	-		
			3.00	V-0	130	115	140	0	0	1	6	1	-	-		
<b>Latamid 66 H2 G/35-V0KB1 (q) (r)</b>		ALL	0.75	HB	130	115	150	3	0	-	-	-	-	-		
			1.50	V-0	130	115	150	1	0	-	-	-	-	-		
			3.00	V-0	130	115	150	0	0	1	6	0	-	-		
<b>Latamid 66 H2 G/50-V0KB1 (q) (r)</b>		NC,BK	0.86	V-0	110	100	115	0	1	-	-	-	-	-		
			1.00	V-0	110	105	120	0	1	-	-	-	800	960		
			1.50	V-0	110	105	120	0	1	-	-	-	800	960		
			2.00	V-0	110	105	120	0	1	-	-	-	800	960		
			3.00	V-0	110	105	120	0	1	0	6	0	800	960		
<b>Latamid 66 H2 G/25-V0KB3 (q) (r)</b>		NC,BK,GY	0.75	HB	110	100	120	2	0	-	-	-	-	-		
			1.50	V-0	110	100	120	0	0	-	-	-	-	-		
			3.00	V-0	110	110	120	0	0	1	5	0	-	-		
<b>Latamid 66 H2 G/35-V0KB3 (q) (r)</b>		NC,BK	1.50	V-0	130	115	140	0	0	-	-	-	-	-		
			3.00	V-0	130	115	140	0	0	0	5	0	-	-		
<b>Latamid 66 H2 G/25-V0KB4 (q) (r)</b>		NC,BK,GY,GN	0.75	V-0	-	130	130	0	0	-	-	-	-	-		
			0.90	V-0	130	130	130	0	0	-	-	-	-	-		
			1.00	V-0	130	130	130	0	0	-	-	-	775	960		
			2.00	V-0	130	130	130	0	0	-	-	-	800	960		
			3.00	V-0	130	130	130	0	0	-	-	0	800	960		

Product Material		R.T.I.													
					Elec		Mech		H			D		G	
		Colors	Min Thk mm	UL 94 Flame Class	With Imp	w/o Imp	H W	H A	H V	D 4	C 9	G T	G W	G I	G F
Latamid 66 H2 G/25-V0CT1 (q) (r)	NC	0.40	V-2	65	65	65	-	-	-	-	-	-	-	-	
	NC, BK	0.50	V-2	130	65	65	0	0	-	-	-	-	-	-	
	ALL	0.71	V-0	140	120	130	0	0	-	-	-	-	850	960	
		1.50	V-0	140	120	130	0	0	-	-	-	-	850	960	
		2.00	V-0	140	120	130	0	0	-	-	-	-	900	960	
	3.00	V-0	140	120	130	0	0	1	6	1	900	960			
dielectric strength = 13 kV/mm volume resistivity = 10x10^10 ohm-cm ball pressure test IEC60695-10-2 = 165°C															
Latamid 66 H2 G/25-V0HF1 (q) (r)	GY	0.50	HB	65	65	65	-	-	-	-	-	-	-	-	
	ALL	0.75	V-0	-	130	130	0	0	-	-	-	-	-	-	
		0.90	V-0	130	130	130	0	0	-	-	-	-	-	-	
		1.50	V-0	130	130	130	0	0	-	-	-	775	960		
	3.00	V-0	130	130	130	0	0	-	-	0	800	960			
Latamid 66 H2 G/25-V0CT4 (q) (r)	NC,RD,BK	0.75	V-0	65	65	65	0	1	-	-	-	-	-		
	ALL	0.75	V-1	65	65	65	0	1	-	-	-	-	-		
		1.50	V-0	65	65	65	0	1	-	-	-	-	-		
	3.00	V-0	65	65	65	0	1	-	-	0	-	-			
Latamid 66 H2 G/25-V0HF (q) (r)	ALL	0.75	V-0	65	65	65	-	-	-	-	-	-	-		
Latamid 66 H2 G/20-V2 (q) (r)	ALL	0.75	V-2	65	65	65	-	-	-	-	-	850	960		
		1.00	V-2	65	65	65	-	-	-	-	-	800	960		
		2.00	V-2	65	65	65	-	-	-	-	-	900	960		
		3.00	V-2	65	65	65	-	-	-	-	2	900	960		
Kelon A FR H2 CEG/250-V0 (q) (r)	ALL	0.74	HB	65	65	65	-	-	-	-	-	-	-		
		1.50	V-0	65	65	65	-	-	-	-	-	-	-		
Kelon A FR H2 CETG/300-V0 (q) (r)	ALL	0.74	V-0	130	100	120	0	0	-	-	-	-	-		
		1.00	V-0	130	100	120	0	0	-	-	-	850	960		
		1.10	V-0	130	100	120	0	0	-	-	-	-	-		
		1.50	V-0	130	100	130	0	0	-	-	-	850	960		
	3.00	V-0	130	100	130	0	0	2	6	2	900	960			
Kelon A FR H2 CET/35-V2 (q) (r)	ALL	0.71	V-2	140	100	140	0	0	-	-	-	-	-		
		1.50	V-2	140	100	140	0	0	-	-	-	800	960		
		3.00	V-2	140	105	140	0	0	0	5	1	825	960		
Kelon A FR H2 CER/25-V2HF (q) (r)	ALL	0.80	V-2	65	65	65	-	-	-	-	-	-	-		
PA66/6 Latamid 68 H2-V0 (q) (r)	ALL	0.41	V-0	65	65	65	4	0	-	-	-	-	-		
		0.71	V-0	140	95	110	4	0	-	-	-	-	-		
		0.71	V-0	140	95	110	4	0	-	-	-	960	960		
		1.50	V-0	140	95	110	3	0	-	-	-	-	-		
		3.00	V-0	140	95	110	2	0	0	6	0	-	-		
dielectric strength = 22 kV/mm volume resistivity = 11x10^10 ohm-cm ball pressure test IEC60695-10-2 = 165°C comparative tracking index IEC60112 = 550 V															
Latamid 68 H2-V0H (q) (r)	RD,BK	0.75	V-0	130	105	130	4	0	-	-	-	-	-		
		1.50	V-0	130	105	130	3	0	-	-	-	-	-		
		2.00	V-0,5VA	130	105	130	3	0	-	-	-	-	-		
		3.00	V-0,5VA	130	105	130	1	0	1	6	3	-	-		
PA6	Latamid 6 (q) (r)	NC,BK	0.75	V-2	65	65	65	-	-	-	-	-	-		
Latamid 6 BH (q) (r)	ALL	0.75	V-2	140	90	115	4	0	-	-	-	-	-		
		1.50	V-2	140	95	115	4	0	-	-	-	-	-		
		3.00	V-2	140	95	115	3	0	0	5	0	-	-		
Latamid 6 H2 G/10 (q) (r)	ALL	0.75	HB	130	115	140	4	0	-	-	-	-	-		
		1.50	HB	130	115	140	4	0	-	-	-	-	-		
		3.00	HB	130	130	155	4	0	-	5	1	-	-		
Latamid 6 H2 G/30 (q) (r)	ALL	0.71	HB	65	65	65	-	-	-	-	-	-	-		
		0.75	HB	125	115	140	-	-	-	-	-	-	-		
		1.50	HB	125	115	140	4	0	-	-	-	-	-		
	3.00	HB	125	125	155	4	0	0	5	1	-	-			
Latamid 6 H2 G/(s) (q) (r)	ALL	0.75	HB	125	115	140	4	0	-	-	-	-	-		
		1.50	HB	125	115	140	4	0	-	-	-	-	-		
		3.00	HB	125	125	155	4	0	0	5	1	-	-		
Latamid 6 H2 G/50 (q) (r)	ALL	0.75	HB	125	120	150	4	0	-	-	-	-	-		
		1.50	HB	125	120	150	4	0	-	-	-	-	-		
		3.00	HB	125	125	155	4	0	0	5	0	-	-		
Kelon B H CET/30 (q) (r)	ALL	0.71	HB	140	105	140	4	0	-	-	-	-	-		
		1.50	HB	140	105	140	-	-	-	-	-	-	-		
	3.00	HB	140	105	140	3	0	0	6	1	-	-			
Kelon B H CETG/300 (q) (r)	ALL	1.50	HB	65	65	65	-	-	-	-	-	-	-		

		R.T.I.												
		-----												
		Elec			Mech			H	H	H	D	C	G	G
Product	Material	Min Thk mm	UL 94 Flame Class	With Imp	w/o Imp	W I	A I	V T	4 5	9 T	I I	W T	I I	
	Colors	NC	NC	NC	NC	NC	NC	NC	NC	NC	NC	NC	NC	
Latamid 6 H2 PX-V0 (q) (r)	NC	1.00	V-0	65	65	65	-	-	-	-	-	800	960	
		2.00	V-0	65	65	65	-	-	-	-	-	800	960	
		3.00	V-0	65	65	65	-	-	-	-	-	800	960	
Latamid 6 H-V0 (q) (r)	ALL	0.40	V-2	65	65	65	-	-	-	-	-	-	-	
		0.86	V-0	140	105	120	4	0	-	-	-	-	-	
		1.50	V-0	140	105	120	2	0	-	-	-	-	-	
Latamid 6 H2 PX-V2 (q) (r)	NC	0.75	V-2	65	65	65	-	-	-	-	-	825	850	
		1.00	V-2	65	65	65	-	-	-	-	-	825	900	
		2.00	V-2	65	65	65	-	-	-	-	-	825	900	
Latamid 6 G/20-V1 (q) (r)	ALL	1.50	V-1	65	65	65	-	-	-	-	-	-	-	
		3.00	V-0	65	65	65	-	-	-	-	-	-	-	
Latamid 6G/(k)-V1 (q) (r) (see notes)	ALL	1.50	V-1	65	65	65	-	-	-	-	-	-	-	
		3.00	V-0	65	65	65	-	-	-	-	-	-	-	
Latamid 6 G/30-V1 (q) (r)	ALL	1.50	V-1	65	65	65	-	-	-	-	-	-	-	
		3.00	V-0	65	65	65	-	-	-	-	-	-	-	
Latamid 6 H2 G/15-V0 (q) (r)	ALL	1.50	V-0	65	65	65	-	-	-	-	-	-	-	
Latamid 6 H2 G/(I)-V0 (q) (r) (see notes)	ALL	1.50	V-0	65	65	65	-	-	-	-	-	-	-	
Latamid 6 H2 G/30-V0 (q) (r)	ALL	1.50	V-0	65	65	65	-	-	-	-	-	-	-	
Latamid 6 H2 G/20-V2HF (f2) (q) (r)	ALL	0.75	V-2	120	115	115	2	0	-	-	-	775	960	
		1.50	V-2	120	120	120	2	0	-	-	-	725	960	
		3.00	V-2	120	120	120	2	0	1	6	1	-	-	
Latamid 6 H2 G/(k)-V2HF (q) (r)	ALL	0.75	V-2	120	115	115	2	0	-	-	-	-	-	
		1.50	V-2	120	120	120	2	0	-	-	-	-	-	
		3.00	V-2	120	120	120	2	0	1	6	1	-	-	
Latamid 6 H2 G/30-V2HF (q) (r)	ALL	0.75	V-2	130	120	120	2	0	-	-	-	-	-	
		1.50	V-2	130	120	130	1	0	-	-	-	-	-	
		3.00	V-2	130	120	130	0	0	1	6	1	-	-	
Latamid 6 H2 G/30-V0CT1 (q) (r)	ALL	0.75	V-0	130	115	130	0	0	-	-	-	-	-	
		1.50	V-0	130	115	130	0	0	-	-	-	-	-	
		3.00	V-0	130	115	130	0	0	1	5	1	-	-	
Latamid 6 H2 G/20-V0HF1 (q) (r)	WT	0.75	V-2	65	65	65	0	4	-	-	-	-	-	
	BK	0.75	V-0	65	65	65	0	4	-	-	-	-	-	
	WT, BK	1.50	V-0	65	65	65	0	0	-	-	-	-	-	
	WT, BK	3.00	V-0	65	65	65	0	0	-	-	1	-	-	
Latamid 6 H2 G/30-V0HF1 (q) (r)	ALL	0.75	V-0	-	130	130	0	0	-	-	-	-	-	
		0.90	V-0	130	130	130	0	0	-	-	-	-	-	
		1.00	V-0	130	130	130	0	0	-	-	-	775	960	
		2.00	V-0	130	130	130	0	0	-	-	-	775	960	
Kelon B FR H CET/05-V2HF (q) (r)	ALL	0.71	V-2	65	65	65	-	-	-	-	-	-	-	
		0.71	V-2	140	105	140	0	0	-	-	-	-	-	
		1.50	V-0	140	105	140	0	0	-	-	-	-	-	
Kelon B FR H CET/30-V0 (q) (r)	ALL	0.75	V-0	140	120	140	0	0	-	-	-	-	-	
		1.50	V-0	140	120	140	0	0	-	-	-	-	-	
		3.00	V-0	140	120	140	0	0	0	6	2	-	-	
Kelon B FR H2 CEG/500-V0CT3 (q) (r)	ALL	0.75	V-1	150	105	130	-	-	-	-	-	-	-	
		1.20	V-0	150	110	140	0	0	-	-	-	-	-	
		3.00	V-0	150	120	140	0	0	-	-	0	-	-	
Kelon B FR H2 CE/25-V2HF (q) (r)	ALL	0.70	V-2	65	65	65	-	-	-	-	-	-	-	
PPA Laramid G/30-V0HF1 (q) (r)	ALL	0.75	V-0	50	50	50	0	2	-	-	-	-	960	
		1.50	V-0	50	50	50	0	1	-	-	-	-	960	
		3.00	V-0	50	50	50	0	1	-	6	0	825	960	
PP Latene	AG7H G/30 (q) (r)	ALL	1.50	HB	65	65	65	-	-	-	-	-	-	
	AG20H G/40 (q) (r)	ALL	0.75	HB	65	65	65	-	-	-	-	-	-	
	9H TES/30 (q) (r)	ALL	1.50	HB	65	65	65	-	-	-	-	-	-	
	7H2W TR/40 (q) (r)	ALL	1.5-2.7	HB	65	65	65	-	-	-	-	-	-	
	7 T/40 (q) (r)	GY	1.5-2.7	HB	65	65	65	-	-	-	-	-	-	
	22H2 MX/25 (q) (r)	ALL	1.50	HB	65	65	65	-	-	-	-	-	-	
	3.00	HB	65	65	65	-	-	-	-	-	-	-		
	9-V0 FE66 (q) (r)	NC,(BN)	1.80	V-0	65	65	65	-	-	-	-	-	-	
	7 TR-V2 (q) (r)	ALL	0.75	V-2	65	65	65	-	-	-	-	-	-	
	7-V2 (q) (r)	ALL	1.50	V-2	65	65	65	-	-	-	-	-	-	
			3.00	V-2	65	65	65	-	-	-	-	-	-	

		R.T.I.													
		Elec					Mech		H	H	H	D	C	G	G
Product	Material	Min	UL 94				H	H	V	4	9	T	W	W	
	Colors	Thk	Flame	Imp	Imp	Imp	W	A	T	5	5	I	I	I	
		mm	Class	With	w/o		I	I	R				T	F	
	Latene 7 H2-V2HF	0.75	V-2	65	65	65	-	-	-	-	0	-	-	-	
		1.00	V-2	65	65	65	-	-	-	-	-	775	960	-	
		2.00	V-2	65	65	65	-	-	-	-	-	775	960	-	
		2.10	V-2	65	65	65	-	-	-	-	-	-	-	-	
		0.55	V-2	65	65	65	4	0	-	-	-	-	-	-	
	Latene 7H2W-V0 (q) (r)	BK	V-2	65	65	65	4	0	-	-	-	-	-	-	
		NC,BK	V-2	65	65	65	4	0	-	-	-	825	960	-	
		1.50	V-0	110	115	115	2	0	-	-	-	825	960	-	
		3.00	V-0	110	115	115	1	0	1	6	0	825	960	-	
	Latene 1H2W-V0 (q) (r)	ALL	V-0	110	115	115	2	0	-	-	-	-	-	-	
		3.00	V-0	110	115	115	1	0	1	6	0	-	-	-	
	Latene (1-30)H2W-V0 (q) (r)	ALL	V-0	110	115	115	2	0	-	-	-	-	-	-	
	(see notes)	3.00	V-0	110	115	115	1	0	1	6	0	-	-	-	
	Latene 30H2W-V0 (q) (r)	ALL	V-0	110	115	115	2	0	-	-	-	-	-	-	
		3.00	V-0	110	115	115	1	0	1	6	0	-	-	-	
		0.75	V-0	100	100	100	3	0	1	-	-	-	-	-	
	Latene 7H2W T-V0 (q) (r)	ALL	V-0	100	100	100	3	0	1	-	-	-	-	-	
		1.50	V-0	100	100	100	2	0	1	6	0	-	-	-	
		3.00	V-0	100	100	100	2	0	1	6	0	-	-	-	
		WT, GY	5VA	100	100	100	3	0	-	-	-	-	-	-	
		0.75	V-0	65	65	65	4	2	-	-	-	-	-	-	
	Latene 7H2W T-V0E (q) (r)	ALL	V-0	65	65	65	3	0	-	-	-	-	-	-	
		1.50	V-0	65	65	65	3	0	-	-	-	-	-	-	
		2.00	V-0,5VB	65	65	65	3	0	-	-	-	-	-	-	
		3.00	V-0,5VB	65	65	65	2	0	-	-	-	-	-	-	
	Latene 7 T-V0 (q) (r)	NC	V-0	65	65	65	-	-	-	-	-	-	-	-	
		3.00	V-0	65	65	65	-	-	-	-	-	-	-	-	
	Latene 7 G/25-V0 (q) (r)	NC	V-0	65	65	65	-	-	-	-	-	-	-	-	
	Latene AG3H2W G/30-V0 (q) (r)	ALL	V-0	65	65	65	-	-	-	-	-	-	-	-	
		0.89	V-0	65	65	65	-	-	-	-	-	-	-	-	
		3.00	5VA	65	65	65	-	-	-	-	-	-	-	-	
	Latene AG3H2W G/30-V0 (f2) (q) (r)	BK	-	65	65	65	-	-	-	-	-	-	-	-	
	Latene AG7H2 G/30-V0HF (q) (r)	BK	V-0	65	65	65	-	-	-	-	-	-	-	-	
	Latene EP 7-V2 (q) (r)	ALL	V-2	65	65	65	-	-	-	-	-	-	-	-	
	Latene EP 3H-V0 (q) (r)	YL	V-0	65	65	65	-	-	-	-	-	-	-	-	
ABS	Lastilac SP G/05 (q) (r)	ALL	HB	60	60	60	-	-	-	-	-	-	-	-	
	Lastilac SP G/ (c) (q) (r) (see notes)	ALL	HB	60	60	60	-	-	-	-	-	-	-	-	
	Lastilac SP G/30 (q) (r)	ALL	HB	60	60	60	-	-	-	-	-	-	-	-	
	Lastilac RT-HB (q) (r)	ALL	HB	60	60	60	-	-	-	-	-	-	-	-	
	Lastilac RT S/20 (q) (r)	ALL	HB	60	60	60	-	-	-	-	-	-	-	-	
		1.50	HB	60	60	60	-	-	-	-	-	-	-	-	
		3.00	HB	60	60	60	-	-	-	-	-	-	-	-	
	Lastilac AR-V0 (q) (r)	ALL	V-0	60	60	60	-	-	-	-	-	-	-	-	
		3.30	5VA	60	60	60	-	-	-	-	-	-	-	-	
	Lastilac AR-V0E (q) (r)	ALL	V-0	60	60	60	-	-	-	-	-	-	-	-	
		1.50	V-0	60	60	60	-	-	-	-	-	-	-	-	
		3.00	V-0	60	60	60	-	-	-	-	-	-	-	-	
	Lastilac ARUV-V0 (q) (r)	ALL	V-0	60	60	60	3	0	-	-	-	-	-	-	
		3.30	5VA	60	60	60	2	0	3	6	1	-	-	-	
	Lastilac TR1-V0 (q) (r)	NC	V-0	60	60	60	-	-	-	-	-	-	-	-	
	Lastilac AR G/(d)-V0 (q) (r) (see notes)	ALL	V-0	60	60	60	-	-	-	-	-	-	-	-	
	Lastilac AR G/30-V0 (q) (r)	ALL	V-0	60	60	60	-	-	-	-	-	-	-	-	
Alloys	Lastilac 11 G/10 (q) (r)	NC	HB	60	60	60	-	-	-	-	-	-	-	-	
	Lastiflex AR-V0 (q) (r)	ALL	V-0	50	50	50	-	-	-	-	-	-	-	-	
		0.71	V-0	50	50	50	-	-	-	-	-	-	-	-	
		3.00	5VA	50	50	50	-	-	-	-	-	-	-	-	
PS	Lastirol R-V0 (q) (r)	NC	V-2	50	50	50	-	-	-	-	-	-	-	-	
		3.00	V-0	50	50	50	-	-	-	-	-	-	-	-	
	Lastirol R-V2 (q) (r)	NC	V-2	50	50	50	-	-	-	-	-	-	-	-	
		1.60	V-2	50	50	50	-	-	-	-	-	-	-	-	
	Lastirol TR G/10-V1 ES (q) (r)	NC	V-2	50	50	50	-	-	-	-	-	-	-	-	
		3.00	V-2	50	50	50	-	-	-	-	-	-	-	-	
		6.00	V-1	50	50	50	-	-	-	-	-	-	-	-	
	Lastirol TR G/10-HB ES (q) (r)	NC, BK	HB	50	50	50	-	-	-	-	-	-	-	-	
PPOm	Laril 13-V1 (q) (r)	NC, BK	V-1	50	50	50	-	-	-	-	-	-	-	-	
	Laril 13-V1KC (q) (r)	GY	V-1	50	50	50	-	-	-	-	-	-	-	-	
		1.50	V-1	50	50	50	-	-	-	-	-	-	-	-	
		6.00	V-0	50	50	50	-	-	-	-	-	-	-	-	
	Laril 13 G/(a)-V1 (q) (r) (see notes)	NC	V-1	50	50	50	-	-	-	-	-	-	-	-	
		1.50	V-1	50	50	50	-	-	-	-	-	-	-	-	
		6.00	V-0	50	50	50	-	-	-	-	-	-	-	-	
	Laril 13 G/20-V1 (q) (r)	GY,NC, BK	V-1	50	50	50	-	-	-	-	-	-	-	-	
		1.50	V-1	50	50	50	-	-	-	-	-	-	-	-	
		NC	V-0	50	50	50	-	-	-	-	-	-	-	-	
PC	Latilon 24D-V2 (q) (r)	ALL	V-2	80	80	80	-	-	-	-	-	-	-	-	
		1.00	V-2	80	80	80	-	-	-	-	-	-	-	-	
		2.50	V-2	80	80	80	-	-	-	-	-	-	-	-	
	Latilon 26D-V2 (q) (r)	ALL	V-2	80	80	80	-	-	-	-	-	-	-	-	
		1.00	V-2	80	80	80	-	-	-	-	-	-	-	-	
		2.50	V-2	80	80	80	-	-	-	-	-	-	-	-	

Product Material		R.T.I.												
		Colors		Elec		Mech		H W	H A	H V	D 4	C T	G W	G W
				Min Thk mm	UL 94 Flame Class	With Imp	w/o Imp							
	Latilon 28D-V2 (q) (r)	ALL	1.00	V-2	80	80	80	-	-	-	-	-	-	-
			2.50	V-2	80	80	80	-	-	-	-	-	-	-
	Latilon 30D-V2 (q) (r)	ALL	1.00	V-2	80	80	80	-	-	-	-	-	-	-
			2.50	V-2	80	80	80	-	-	-	-	-	-	-
	Latilon 28-V0 (q) (r)	ALL	0.89	V-2	80	80	80	-	-	-	-	-	-	-
			3.00	V-0	80	80	80	-	-	-	-	-	-	-
	Latilon 28D-V0 (q) (r)	ALL	0.89	V-2	80	80	80	-	-	-	-	-	-	-
			3.00	V-0	80	80	80	-	-	-	-	-	-	-
	Latilon 30-V0 (q) (r)	NC	0.91	V-2	80	80	80	-	-	-	-	-	-	-
			1.70	V-0	80	80	80	-	-	-	-	-	-	-
	Latilon 30D-V0 (q) (r)	NC	0.91	V-2	80	80	80	-	-	-	-	-	-	-
			1.70	V-0	80	80	80	-	-	-	-	-	-	-
	Latilon 28D G/(e) (q) (r) (see notes)	ALL	1.50	V-1	80	80	80	-	-	-	-	-	-	-
			6.00	V-0	80	80	80	-	-	-	-	-	-	-
	Latilon 30D G/10-V0 (q) (r)	ALL	0.89	V-2	80	80	80	-	-	-	-	-	-	-
			1.70	V-0	80	80	80	-	-	-	-	-	-	-
	Latilon 28D G/20-V0 (q) (r)	GN	0.60	HB	80	80	80	-	-	-	-	-	-	-
		ALL	1.50	V-0	80	80	80	-	-	-	-	-	-	-
PBT	Later 4 G/15 (q) (r)	ALL	0.75	HB	140	130	140	4	0	-	-	-	-	-
			1.50	HB	140	130	140	2	0	-	-	-	-	-
			3.00	HB	140	130	140	0	0	0	5	2	-	-
	Later 4 G/(l) (q) (r) (see notes)	ALL	0.75	HB	130	130	140	4	0	-	-	-	-	-
			1.50	HB	130	130	140	2	0	-	-	-	-	-
			3.00	HB	130	130	140	0	0	1	6	2	-	-
	Later 4 G/30 (q) (r)	ALL	0.75	HB	130	130	140	3	0	-	-	-	-	-
			1.50	HB	130	130	140	1	0	-	-	-	-	-
			3.00	HB	130	130	140	0	0	1	6	1	-	-
	Later 4 CE/50 (q) (r)	NC	0.71	HB	75	75	75	-	-	-	-	-	-	-
	Later 4-V0 (q) (r)	ALL	0.75	V-0	140	130	140	4	0	-	-	-	-	-
			1.50	V-0	140	130	140	3	0	-	-	-	-	-
			3.00	V-0	140	130	140	2	0	4	6	2	-	-
	Later 4 G/10-V0 (q) (r)	ALL	0.75	V-0	130	120	120	4	0	-	-	-	-	-
			1.50	V-0	130	120	120	3	0	-	-	-	-	-
			3.00	V-0	130	130	130	2	0	4	6	2	-	-
	Later 4 G/(i)-V0 (q) (r) (see notes)	ALL	0.75	V-0	130	120	120	4	0	-	-	-	-	-
			1.50	V-0	130	120	120	3	0	-	-	-	-	-
			3.00	V-0	130	130	130	2	0	4	6	2	-	-
	Later 4 G/30-V0 (q) (r)	ALL	0.75	V-0	140	130	130	3	0	-	-	-	-	-
			1.50	V-0	140	130	130	2	0	-	-	-	-	-
			3.00	V-0	140	130	140	0	0	4	6	2	-	-
	Later 4 G/30-V0CT1 (q) (r)	NC	0.75	V-0	75	75	75	-	-	-	-	-	-	-
			1.50	V-0	75	75	75	-	-	-	-	-	-	-
			3.00	V-0	75	75	75	-	-	-	5	1	-	-
	Later 4 G/30-V0CT2 (q) (r)	NC	0.75	V-0	75	75	75	-	-	-	-	-	-	-
			3.00	V-0	75	75	75	-	-	-	5	1	-	-
	Later 4 G/30-V0GW (q) (r)	ALL	0.75	V-0	75	75	75	0	2	-	-	-	-	-
			1.00	V-0	75	75	75	0	2	-	-	-	930	960
			1.50	V-0	75	75	75	0	1	-	-	-	930	960
			3.00	V-0	75	75	75	0	0	-	6	0	960	960
	Later 4 G/30-V0HF1 (q) (r)	ALL	0.75	V-0	75	75	75	0	1	-	-	-	-	-
			1.00	V-0	75	75	75	0	1	-	-	-	825	960
			1.50	V-0	75	75	75	0	0	-	-	-	825	960
			3.00	V-0	75	75	75	0	0	-	5	0	960	960
	Later 4E61 GCER/450-V0 (q) (r)	GY	0.75	V-0	75	75	75	3	0	-	-	-	-	-
			1.50	V-0	75	75	75	2	0	-	-	-	-	-
			3.00	V-0	75	75	75	1	0	0	4	1	-	-
POM	Latan 9 (q) (r)	NC	1.50	HB	50	50	50	-	-	-	-	-	-	-
	Latan 13 S/30 (q) (r)	ALL	1.50	HB	50	50	50	-	-	-	-	-	-	-
PPS	Larton G/40 (q) (r)	NC, BK	0.42	V-0	130	130	130	-	-	-	-	-	-	-
			0.75	V-0	130	130	130	5	0	-	-	-	-	-
			1.50	V-0	130	130	130	4	0	-	-	-	-	-
			3.00	V-0	130	130	130	0	0	-	-	-	-	-
	Larton GCE/600 (q) (r)	NC, BK	0.75	V-0	130	130	130	3	1	-	-	-	-	-
			1.50	V-0	130	130	130	3	1	-	-	-	-	-
			3.00	V-0	130	130	130	0	1	-	-	-	-	-
	Larton GCE/650 (q) (r)	ALL	0.75	V-0	130	130	130	3	3	-	-	-	-	-
			1.50	V-0	130	130	130	0	0	-	-	-	-	-
			3.00	V-0	130	130	130	0	0	-	-	-	-	-
	Larton L G/40 (q) (r)	NC	0.75	V-0	130	130	130	-	-	-	-	-	-	-
PSU	Lasulf (q) (r)	ALL	1.50	HB	50	50	50	-	-	-	-	-	-	-

Product Material		R.T.I.											
		Elec		Mech		H W	H A	H V	D 4	C T	G W	G W	
		Min Thk mm	UL 94 Flame Class	With Imp	w/o Imp								
Colors				I	I	R	5	I	T	I			
<b>SPECIALS</b>													
PA6	Latilub 62-01M G/30 (q) (r)	NC, (BK)	0.86	HB	65	65	65	-	-	-	-	-	-
			0.75	HB	120	100	110	3	0	-	-	-	-
PA66	Latilub 66-20T G/20 (q) (r)	ALL	1.50	HB	120	100	110	0	0	-	-	-	-
			3.00	HB	120	100	115	0	0	0	6	0	-
	Latilub 66-01M (q) (r)	NC	0.72	HB	65	65	65	-	-	-	-	-	-
	Latilub 66-01M G/(a) (q) (r) (see notes)	NC	0.72	HB	65	65	65	-	-	-	-	-	-
	Latilub 66-01M G/30 (q) (r)	NC	0.72	HB	65	65	65	-	-	-	-	-	-
PA12	Latamid 12 H FE90:0081 (q) (r)	NC,(BK)	0.71- 3.00	HB	65	65	65	-	-	-	-	-	-
			1.50	HB	80	80	80	-	-	-	-	-	-
PC	Latilub 87/28-20T (q) (r)	NC,BK	3.00	V-1	80	80	80	-	-	-	-	-	-
			6.00	V-0	80	80	80	-	-	-	-	-	-
	Latilub 87/24UV-20T (q) (r)	GY	0.75	HB	80	80	80	-	-	-	-	-	-
			1.40	HB	80	80	80	-	-	-	-	-	-
	Latilub 87/28-12T G/20 (q) (r)	NC,BK	3.00	V-1	80	80	80	-	-	-	-	-	-
			6.00	V-0	80	80	80	-	-	-	-	-	-
PBT	Latilub 75/4-05T G/30-V0 (q) (r)	BK	0.75	HB	75	75	75	3	0	-	-	-	-
			1.50	V-0	75	75	75	2	0	-	-	-	-
			3.00	V-0	75	75	75	1	0	-	-	-	-
			dielectric strength = 30 kV/mm volume resistivity = 11x10^10 ohm-cm										
POM	Latilub 73/13-20T (q) (r)	NC,BK	1.50	HB	50	50	50	-	-	-	-	-	-
			1.50	HB	50	50	50	-	-	-	-	-	-
	Latilub 73/13-15T G/15 (q) (r)	NC	3.00	HB	50	50	50	-	-	-	-	-	-
PPS	Latilub 80-15T G/30 (q) (r)	NC,BK	0.74	V-0	130	130	130	-	-	-	-	-	-
			0.74	V-0	130	130	130	-	-	-	-	-	-
	Latilub 80-10T Y/15 (q) (r)	NC	3.00	V-0	130	130	130	-	-	-	-	-	-
PA/PP	Latiblend 6252 H2 G/30 (q) (r)	ALL	0.75	HB	50	50	50	-	-	-	-	-	-
PA6	Latiohm 63-08 PD02 G/25 (q) (r)	BK	0.75	HB	65	65	65	-	-	-	-	-	-
		BK	3.00	HB	65	65	65	-	-	-	-	-	-
			0.75	HB	65	65	65	-	-	-	-	-	-
PA66	Latiohm 66-07 PD08 G/30 (q) (r)	BK	1.50	HB	65	65	65	-	-	-	-	-	-
			3.00	HB	65	65	65	-	-	-	-	-	-
			0.75	V-1	150	105	130	-	-	-	-	-	-
PA6	Laticonther 62 CEG/500-V0HF1 (q) (r)	ALL	1.20	V-0	150	110	140	0	0	-	-	-	-
			3.00	V-0	150	120	140	0	0	-	-	0	-
<b>AVVERTENZE</b>													
LATI non garantisce che i dati contenuti in questa lista sono attuali, completi e privi di errori. Per verificare i valori si raccomanda vivamente agli utenti di contattare l'Assistenza Tecnica Clienti o la rete commerciale LATI. LATI Industria Termoplastici S.p.A. declina ogni responsabilità insorgente dall'uso delle informazioni descritte in questo documento.													
Copyright © 1999 LATI S.p.A. - All Rights Reserved													